



## CONDENSED SPEC SHEET\*


Grade Name: ART MAESTRO

SUBSTANCE (GSM)	CALIPER (μM)	BENDING RESISTANCE(L&W) mN		
		Tappi T556		
Tappi T 410	Tappi T 411	MD	CD	GM
200	188	49	25	35
210	197	55	27	39
220	207	69	34	48
230	216	78	39	55
250	235	108	54	76
260	244	118	59	83
270	254	137	69	97
280	263	147	74	104
300	282	177	88	125
TOL : ± 5%	± 5%			-15%

CERTIFICATIONS & COMPLIANCES	
Manufacturing	ISO 9001, ISO 14001, ISO 45001, BRC Global Standard
Environmental & Safety	FSC® CoC, Light ECF, CII GreenCo Platinum, SMETA 4 Pillar
Regulatory	REACH, ROHS

PARAMETER	UNITS	VALUE
ROUGHNESS - PPS (Avg.) TOP BACK	μm	2.0 (+ 0.5) 3.0 (+ 0.5)
BRIGHTNESS ISO TOP & BACK	%	90 MIN
WHITENESS CIE TOP & BACK	%	110 MIN
SURFACE STRENGTH IGT PICK (MED.VISCOSITY) TOP & BACK	m/sec	0.7 MIN
GLOSS AT 75° (Avg.) TOP BACK	%	40 MIN 30 MIN
MOISTURE	%	5.5 ± 1.0

### CONSTRUCTION



#### Note :

- All Properties are according to ITC PSPD Measurements
- Test Climate 23°C ± 1 & 50% ± 2 RH
- Tolerances are based upon 95% Confidence limits of single mill measurements of conditioned random samples
- All parameters are measured as per relevant Tappi standards



GARMENTS



PUBLISHING



DIGITAL



CULTURAL /  
CARDS